

# MOLYKOTE<sup>®</sup> HP-800 Grease

Electrically conductive PFPE grease

## Features

- Good compatibility with plastics and rubber
- Wide service-temperature range: -30 to 250°C
- Good electrical conductivity
- No negative effect on electrical contacts

## Benefits

- Good electrical conductivity will aid in dissipating static electricity from lubricated components

## Composition

- Perfluoropolyether oil
- Additives

## Applications

Lubrication of plastic parts in automobiles, electric equipment, audio-visual equipment, precision equipment, office equipment, etc. where electrical conductivity is desired.

## How to use

Clean point of lubrication. As is usual with lubricating grease, apply or fill by means of brush, spatula, or automatic dispensing equipment.

## Handling precautions

This product is chemically inert and nontoxic. However, decomposed gas at over 250°C is hazardous. Ventilation is required when decomposition is expected.

PRODUCT SAFETY INFORMATION REQUIRED FOR SAFE USE IS NOT INCLUDED IN THIS DOCUMENT. BEFORE HANDLING, READ SAFETY DATA SHEETS AND CONTAINER LABELS FOR SAFE USE, PHYSICAL AND HEALTH HAZARD INFORMATION.

## Usable life and storage

When stored in unopened containers, this product has a usable life of 36 months from the date of production.

## Packaging

This product is available in 500 g cans.

## Typical properties

Specification writers: These values are not intended for use in preparing specifications. Please contact your local MOLYKOTE<sup>®</sup> sales representative prior to writing specifications on this product.

Standard <sup>(1)</sup>	Test	Unit	Result
	Appearance	Color	Black
ASTM D445	Viscosity (40°C)	mm <sup>2</sup> /s	420
JIS K 2220	Penetration (unworked)	mm/10	230
	NLGI Class		3
	Service temperature range	°C	-30 to 250
JIS K 2220	Dropping point	°C	None
FTM 791-321	Bleed (200°C/24 hours)	%	7.5
FTM 791-321	Evaporation (200°C/24 hours)	%	0.5
	Volume resistivity (DCAL method)	Ω•cm	4x10 <sup>2</sup>

<sup>(1)</sup>ASTM: American Society for Testing and Materials. JIS: Japanese Industrial Standard. FTM: Federal Test Method Standard.

*DuPont™, the DuPont Oval Logo, and all trademarks and service marks denoted with ™, SM or ® are owned by affiliates of DuPont de Nemours, Inc. unless otherwise noted.  
© 2003-2019 DuPont.*

The information set forth herein is furnished free of charge and is based on technical data that DuPont believes to be reliable and falls within the normal range of properties. It is intended for use by persons having technical skill, at their own discretion and risk. This data should not be used to establish specification limits nor used alone as the basis of design. Handling precaution information is given with the understanding that those using it will satisfy themselves that their particular conditions of use present no health or safety hazards. Since conditions of product use and disposal are outside our control, we make no warranties, express or implied, and assume no liability in connection with any use of this information. As with any product, evaluation under end use conditions prior to specification is essential. Nothing herein is to be taken as a license to operate or a recommendation to infringe on patents.